

# **LOW ORDER WAVEPLATES**

- Thickness 0.15-0.35 mm
- Thinner than multiple order

Low order plates are less temperature sensitive and temperature dependent than multiple order plates. These plates are suitable for high and low power applications.

Movelenath	Retardation λ/2		Retardation λ/4	
Wavelength, nm	Catalogue number	Price, EUR	Catalogue number	Price, EUR
1064	461-4205	160	461-4405	160
532	461-4230	160	461-4430	160
355	461-4240	192	461-4440	192
266	461-4245	196	461-4445	196

#### **SPECIFICATIONS**

Material	Single crystal quartz		
Optical axis	normal to facet on circumference of retarder		
Clear aperture	Ø17 mm (others dimensions on request)		
Ring mount outer diameter	25.4 +0.0 / -0.2 mm		
Nominal thickness of waveplate	0.15–0.35 mm		
Wavefront distortion	λ/10 @ 633 nm		
Surface quality	20-10 scratch & dig (MIL-PRF-13830B)		
Parallelism	< 10 arcsec		
AR coating	R < 0.4%		
Damage threshold	10 J/cm <sup>2</sup> , 10 nsec pulse, 1064 nm typical		

### **RELATED PRODUCTS**

Low Order	High Precision
Plates	Rotation Polarizer,
of other	Waveplate Mount
wavelengths	840-0186
See page 1.54	See page 8.88



# **MULTIPLE ORDER WAVEPLATES**

- Polished to 1-1.5 mm thickness
- Made from a single crystalline plate


Multiple order plates are more dependent on the temperature changes than zero order plates. A change of  $\pm 1\%$  from the designed wavelength of multiple order plate can result in difficulties in retardation. Contrary, with zero order plates  $\pm 1\%$  and even  $\pm 2\%$  change from the designed wavelength can cause only small retardation change.


# **RELATED PRODUCTS**

Multiple Order Plates of other wavelengths
See page 1.54

Adjustable Polarizer Holder of Side Drive 840-0195 See page 8.91







#### **SPECIFICATIONS**

Material	Single crystal quartz		
Optical axis	Normal to facet on circumference of retarder		
Clear aperture	Ø17 mm (others dimensions on request)		
Ring mount outer diameter	25.4 +0.0 / -0.2 mm		
Nominal thickness of waveplate	0.8–1.5 mm		
Surface quality	20-10 scratch & dig (MIL-PRF-13830B)		
Wavefront distortion	λ/10 @ 633 nm		
Parallelism	< 10 arcsec		
AR coating	R < 0.4%		
Damage threshold	10 J/cm <sup>2</sup> , 10 nsec pulse, 1064 nm typical		

Wavelength,	Retardation λ/2		Retardation	Retardation λ/4	
nm	Catalogue number	Price, EUR	Catalogue number	Price, EUR	
1064	462-4205	138	462-4405	138	
532	462-4230	138	462-4430	138	
355	462-4240	143	462-4440	143	
266	462-4245	153	462-4445	153	